

Technical Data Sheet

4M wood insulator hardener

Characteristic properties

Hardener for wood insulator used with wood insulator to give high hardness, flexibility and chemical resistance to atmospheric factors

Materials for application

- wood insulator
- wood insulator hardener

Suitable substrate and surface preparation

The surface must be well prepared and sanded

The surface must be dry, smooth, free from dust and grease.

Suitable for painting wooden surfaces, windows, cupboards, boats and wooden kitchens.

As well as previously painted surfaces after removing all crusts and pimples.

Mixing ratio

Wood insulator	wood insulator hardener
100	100

Pot life

5-6 hours at 20 °C

Drying times at 20°C

initial dryness : 60 min.

final dry: 3 – 4 hours

Certified in ISO 9001, ISO 14001, ISO 45001

For additional information Kindly contact us at info@4mcoatings.com

www.4MCoatings.com



Technical Data Sheet

4M wood insulator hardener

Packaging

0.800kgm

4kgm

color

clear

Expiry

1 years at 20°C

Material safety data

When using these products it is required to comply with the national regulations for health and safety

Certified in ISO 9001, ISO 14001, ISO 45001

For additional information Kindly contact us at info@4mcoatings.com

www.4MCoatings.com